

## Properties of Fused Silica JGS2

Properties	Value		
Transmission Range (Medium transmission ratio)	0.26 ~ 2.10 um (Tavg >85%)		
OH- Content	150 ppm		
Fluorescence (ex 254nm)	Strong v-b		
Impurity Content	20 – 40 ppm		
Birefringence Constant	4 - 6 nm/cm		
Melting Method	Oxy-hydrogen melting		
Density	2.20 g/cm <sup>3</sup>		
Abbe Constant	67.6		
Refractive Index (nd) at 588nm	1.4586		
Hardness	5.5 - 6.5 Mohs' Scale 570 KHN 100		
Design Tensile Strength	4.8 × 10 <sup>7</sup> Pa (N/mm <sup>2</sup> ) (7000 psi)		
Design Compressive Strength	Greater than 1.1 × 10 <sup>9</sup> Pa (160,000 psi)		
Bulk Modulus	3.7 × 10 <sup>10</sup> Pa (5.3 × 10 <sup>6</sup> psi)		
Rigidity Modulus	3.1 × 10 <sup>10</sup> Pa (4.5 × 10 <sup>6</sup> psi)		
Young's Modulus	7.2 × 10 <sup>10</sup> Pa (10.5 × 10 <sup>6</sup> psi)		
Poisson's Ratio	0.17		
Coefficient of Thermal Expansion	5.5 × 10 <sup>-7</sup> cm/cm.°C (20°C – 320 °C)		
Thermal Conductivity	1.4 W/m.°C		
Specific Heat	670 J/kg.°C		
Softening Point	1683 °C		
Annealing Point	1215 °C		
Strain Point	1120 °C		
Electrical Receptivity	7 × 10 <sup>7</sup> ohm.cm (350 °C)		
Dielectric Properties (20°C and 1 MHz) Constant Strength Loss Factor Dissipation Factor	3.75 5 × 10 <sup>7</sup> V/m Less than 4 × 10 <sup>-4</sup> Less than 1 × 10 <sup>-4</sup>		
Velocity of Sound-Shear Wave	3.75 × 10 <sup>3</sup> m/s		
Velocity of Sound/Compression Wave	5.90 × 10 <sup>3</sup> m/s		
Sonic Attenuation	Less than 11 db/m MHz		
Permeability Constants (cm <sup>3</sup> mm/cm <sup>2</sup> sec cm of Hg) Helium Hydrogen Deuterium Neon	(700 °C) 210 × 10 <sup>-10</sup> 21 × 10 <sup>-10</sup> 17 × 10 <sup>-10</sup> 9.5 × 10 <sup>-17</sup>		
Chemical Stability (except hydrofluoric)	High resistance to water and acids		
Wavelength (um)	Refractive Index (n)	Wavelength (um)	Refractive Index (n)
0.2	1.55051	1	1.45042
0.22	1.52845	1.064	1.44962
0.25	1.50745	1.1	1.4492

0.3	1.48779	1.2	1.44805
0.32	1.48274	1.3	1.44692
0.36	1.47529	1.5	1.44462
0.4	1.47012	1.6	1.44342
0.45	1.46557	1.7	1.44217
0.488	1.46302	1.8	1.44087
0.5	1.46233	1.9	1.43951
0.55	1.46008	2	1.43809
0.588	1.4586	2.2	1.43501
0.6	1.45804	2.4	1.43163
0.633	1.45702	2.6	1.42789
0.65	1.45653	2.8	1.42377
0.7	1.45529	3	1.41925
0.75	1.45424	3.2	1.41427
0.8	1.45332	3.37	1.4099
0.85	1.4525	3.507	1.40566
0.9	1.45175	3.707	1.39936

